



Concretes for Agricultural Use

Designated concrete

Revised 2015

Designated concrete

Designated concretes are quality assured designed concretes that conform to a specification detailed in BS 8500 - 2: *Concrete - Complementary British Standard to BS EN 206 - Part 2: Specification for constituent materials and concrete*.

These concretes have been selected to be fit for their intended end uses and they can only be supplied by ready-mixed concrete producers who have the appropriate level of product conformity certification.

A QSRMC or BSI Kitemark Scheme logo on the delivery ticket provides this confirmation. Purchasers can therefore be confident that the concrete will be delivered as specified and ordered.

Selecting the appropriate concrete

Decide which of the 'typical applications' matches your application and site conditions. For foundations, drainage and low rise building use the associated publication *Concretes for housing, Designated Concrete* for selecting the typical application. Identify the recommended designated concrete.

Measure the prepared location and calculate the volume of concrete required. Slightly over-estimate the volume required as it is annoying to run short and expensive to order a very small volume. Have in mind a 'holiday' job for any surplus concrete, e.g. hardstanding.

Ensure a suitable and safe access for the ready-mixed concrete truck, the largest of which may be up to 10.5m long, 2.5m wide and 3.8m high and weigh 32 tonnes when fully loaded.

If the truck cannot discharge directly into the works, provide transport to move the concrete from the delivery truck to the works, e.g. front shovel, or ask the ready-mixed concrete producer for advice. They may be able to provide a truck that has a pump or conveyor or recommend a company that may supply such equipment.



Concrete truck with built-in conveyor system

A few days prior to requiring the concrete, ask for a quotation. Provide the information given below in 'What to specify'. At this stage you may not know the exact volume of concrete so give an estimate and say that you will confirm the volume the day prior to delivery. Confirm the order and time of delivery the day prior to delivery.

What to specify

Specify the designated concrete for the required application, the volume required, the date required and the time when you want the first truck on site. Also specify:

- The nominal maximum aggregate size only if it needs to be different from 20mm (you will get a maximum aggregate size of 20mm if you do not specify a different size). Options, if available, will be 40 or 10mm.
- The slump class as recommended in the Table.

Inform the producer of the intended method of placing and finishing the concrete.

Typical applications for designated concretes

Typical application	Designated concrete	Recommended slump class	
		Hand Compaction	Vibration Equipment
Livestock floors	RC28/35	S3	S2
Stable floors	RC35/45	S3	S2
Crop store floors	RC28/35	S3	S2
Floors (and walls) for silage	RC30/37	S3	S2
Sugar beet storage areas	RC32/40 ^{A)}	S3	S2
Workshop floors and floors subject to small-wheeled forklift trucks	RC32/40	S3	S2
Brewers' grain stores	RC35/45	S3	S2
Mushroom sheds	RC32/40	S3	S2
Toppings for floors such as parlours and dairies	RC35/45 ^{B)}	S2	S2
Floors (and walls) for manure and slurry stores	RC30/37	S3	S2
External yards and roads subject even to occasional de-icing salts	PAV2	S3	S2

^{A)} Where the concrete is subject to even occasional de-icing salts, designated concrete PAV2 is recommended.

^{B)} Take extra care to ensure full compaction of the fresh concrete and proper curing for at least several days.

Health and Safety



Lifting and placing concrete

Ready-mixed concrete is heavy, with a standard barrow load weighing over 100 kg, so lifting/carrying just a small volume may cause physical injury.

It is therefore essential that you follow health and safety regulations in order that you may place, compact and finish the work without straining yourself.


Use of vibrating pokers and equipment

Certain types of plant create a large amount of vibration during use (for example pneumatic hammers, drills, grinders and vibrating pokers).

Prolonged exposure to vibration can cause carpal tunnel syndrome and hand arm vibration syndrome (HAVS).

It is possible to reduce the effects of vibration by selecting plant with vibration dampeners, by using anti-vibration gloves, taking regular breaks and/or by keeping your hands warm in cold weather.

Please seek advice from the manufacturer with regard to the use of this type of equipment. **For advice on safe handling of concrete, placing, compaction and curing of concrete, see 'further reading'.**



Health and safety, BS 8500: Hazard warnings


Where skin is in contact with fresh concrete, skin irritations are likely to occur owing to the alkaline nature of cement. The abrasive effects of sand and aggregate in the concrete can aggravate the condition. Potential effects range from dry skin, irritant contact dermatitis, to - in cases of prolonged exposure - severe burns.

Take precautions to avoid dry cement entering the eyes, mouth and nose when mixing mortar or concrete by wearing suitable protective clothing.

Take care to prevent fresh concrete from entering boots and use working methods that

do not require personnel to kneel in fresh concrete. Unlike heat burns, cement burns might not be felt until some time after contact with fresh concrete, so there might be no warning of damage occurring.

If cement or concrete enters the eye, immediately wash it out thoroughly with clean water and seek medical treatment without delay. Wash wet concrete off the skin immediately. Barrier creams may be used to supplement protective clothing but are not an alternative means of protection.



For further reading refer to

- *British Standards Institution*, BS 8500: 2015. Concrete - Complementary British standard to BS EN 206, Part 1: Method of specifying and guidance for the specifier; Part 2: Specification for constituent materials and concrete, London, BSI.
- *British Standards Institution*, BS 5502-22:2003+A1:2013 Buildings and structures for agriculture - Part 22: Code of practice for design, construction and loading.
- *The Concrete Society*. Good Concrete Guide 8: Concrete Practice, November 2008, Camberley.
- *BRMCA* concretes for Housing, designated concrete. February 2015.



BRMCA is part of the Mineral Products Association, the trade association for the aggregates, asphalt, cement, concrete, dimension stone, lime, mortar and silica sand industries

BRMCA

Gillingham House
38 - 44 Gillingham Street
London SW1V 1HU
Tel +44 (0)20 7963 8000
Fax +44 (0)20 7963 8001
www.brmca.org.uk

All advice or information from The British Ready-Mixed Concrete Association is intended for those who will evaluate the significance and limitations of its contents and take responsibility for its use and application. No liability (including that for negligence) for any loss resulting from such advice or information is accepted. Readers should note that all BRMCA publications are subject to revision from time to time and should therefore ensure that they are in possession of the latest version.

First Published September 2009
This edition June 2015
© MPA

BRMCA Members

Aggregate Industries
www.aggregates.com

Batchmix Ltd, Rotherham Sand & Gravel
www.batchmix.co.uk

Breedon Aggregates
www.breedonaggregates.com

Brett Concrete
www.brett.co.uk

CEMEX UK
www.cemex.co.uk

Hanson UK
hansonready-mixconcrete.co.uk

Hills Quarry Products Ltd
www.hills-group.co.uk

Hope Construction Materials
www.hopeconstructionmaterials.com

J Clubb Ltd

www.jclubb.co.uk

Kendall Ready-Mixed Concrete, Kendall Group
www.kendalls.co.uk

Lafarge Tarmac Ltd
www.lafargetarmac.com

London Concrete
www.aggregate.com

Morris & Perry Ltd
www.morrisandperry.co.uk

Readymix Huddersfield, Myers Group
www.myersgroup.co.uk

Tuck-mix concrete, H Tuckwell & Sons
www.tuckwells.co.uk

Tudor Griffiths Group
www.tgconcrete.co.uk

Affiliates

Bonnar Sand & Gravel
www.bonnar.com

Hillhouse Quarry Group Ltd
www.hillhousegroup.co.uk

Northstone (NI)
www.northstone-ni.co.uk

MPA Scotland
www.mineralproducts.org

QPA NI
www.qpani.org

Printed on recycled paper manufactured at a mill certified with ISO 14001 environmental management standard. The pulp used in this product is bleached using an Elemental Chlorine Free process.